

Product Name: Oxidized Bitumen 75/25

CAS No.: 8052-42-4

HS Code: 271320

Property	Unit	Typical Value
Penetration @ 25°C	dmm	15 – 25
Softening Point (Ring & Ball)	°C	75 ± 5
Flash Point (COC)	°C	> 250
Solubility in Trichloroethylene	%	> 99
Loss on Heating	%	< 0.5
Ductility @ 25°C	cm	< 1
Specific Gravity @ 25°C	—	1.00 – 1.10
Drop Point	°C	180 – 200
Color	—	Black
Form	—	Solid Block / Slab

Technical Note

The values stated are typical and may vary by production batch and conditions. Users are responsible for verifying product suitability for their specific application. No liability is accepted for improper use. Specifications are subject to change without notice.

